

COLOURPLAS HD20

Block Processing Aid & Water Resisting Admixture

PRODUCT DESCRIPTION

Colourplas HD20 (Hydro-dynamic) is a specially formulated processing aid combined with water resisting admixtures, it has been developed to improve compaction and reduce the permeability of concrete as well as improving the dispersion characteristics of the pigments present.

Colourplas HD20 is particularly beneficial in dry or semi-dry concrete.

APPLICATIONS

Colourplas HD20 is used to improve compaction, handling and water resistance of all dry/semi-dry concrete processes for blocks, flags, pavers and other concrete products by improving compaction and forming a permanent hydrophobic layer at the air-concrete interface.

BENEFITS

- Reduced shrinkage.
- Reduced permeability.
- Increased water tightness.
- Reduced efflorescence.
- Improved compaction.
- Improved processing.
- Better surface finish.
- Increased early strength.
- Improved colour.

PROPERTIES

Nature:	Liquid
Appearance:	Light Straw
Specific Gravity: (20°C)	1.04 g/cm ³
pH:	>11.5
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 4.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls—800mls per 100kg cement

(0.20% - 0.80% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE technical department for further advice.

STANDARDS

Colourplas HD20 is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



COLOURPLAS HD20

Block Processing Aid & Water Resisting Admixture

COMPATIBILITY

Colourplas HD20 is compatible with all types of EN 197 cement systems.

Colourplas HD20 should not be premixed with other admixtures and should be batched separately.

STORAGE

Colourplas HD20 should be protected from extreme temperature, frost and direct sunlight, the product has a minimum shelf life of 12 months.

HANDLING

Please refer to the **Colourplas HD20** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

PACKAGING

1000 litre IBC's and bulk deliveries.

NOTES

Colourplas HD20 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Colourplas HD20** may be used after thawing, slowly at room temperature followed by intensive mixing.

Colourplas HD20 is designed for use in dry/semi-dry concrete and masonry mortar, if used in wet concrete over 50mm slump, increases in air entrainment will be observed.

Please consult the OSCRETE technical department for advice on admixture selection.

OSCRETE UK Limited
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 086299
E-mail: technical@oscrete.com
Website: www.oscrete.com

PDS 7933 Rev 03 02/01/2024

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

