

# COLOURPLAS ULTIMA

## Block Processing Aid

### Description

**Colourplas Ultima** benefits the CBP production process by improving compaction. **Colourplas Ultima** will maintain the consistency of the mix and improve the dispersion characteristics of the pigments present, providing more intense colouration. **Colourplas Ultima** effectively reduces the permeability of the concrete units leading to a reduction in the occurrence of efflorescence.

### Applications

**Colourplas Ultima** is used to improve the compaction and handling of all dry/semi dry concrete mix processes for blocks, flags, pavers, tiles and other concrete products. The improved mix properties also result in reduced machine stress and parts wear.

### Benefits in Concrete

- Improved compaction
- Improved processing
- Better surface finish
- Strength increases at all ages
- Improved colour intensity and stability
- Reduced efflorescence



### Properties

Nature	Liquid
Colour	Clear Amber
Specific Gravity	1.01 g/cm <sup>3</sup>
pH	>11.5
Chloride Content	<0.10%
Na <sub>2</sub> O equivalent	<2.00%

### Addition Rates

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 800mls per 100 kg cement  
(0.20% - 0.80% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

### Standards

**Colourplas Ultima** is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



**OSCRETE**  
CONSTRUCTION PRODUCTS



# COLOURPLAS ULTIMA

## Block Processing Aid

### Compatibility

**Colourplas Ultima** is compatible with all types of EN 197 cement systems. **Colourplas Ultima** should not be pre-mixed with other admixtures and should be batched separately.

### Storage

**Colourplas Ultima** should be stored undercover and protected from extreme temperatures, if stored unopened within the range 5°C and 30°C the product will have a minimum shelf life of 12 months.

### Handling

Please refer to the **Colourplas Ultima** Material Safety Data Sheet but in line with normal handling procedures, personal protective equipment should be worn.

### Packaging

200 litre drums, 1000 litre IBCs and bulk deliveries.

### Notes

**Colourplas Ultima** should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Colourplas Ultima** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE Technical Department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd.  
Rutland Street  
Bradford  
West Yorkshire  
BD4 7EA  
United Kingdom

Telephone: +44 (0)1274 393286

Fax: +44 (0)1274 309143

e-mail: [info@oscrete.co.uk](mailto:info@oscrete.co.uk)

Website: [www.oscrete.co.uk](http://www.oscrete.co.uk)

PDS 7534 Rev 03 18/01/2016

#### **Disclaimer**

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.