

OPTOMIX 120

Water Reducing Plasticiser

Description

Optomix 120 is an economical normal range water reducer based upon modified lignosulphonate. It is designed to improve the workability of concrete with minimal effects on other properties. **Optomix 120** if used correctly can achieve water reductions of up to 16%.

Applications

Optomix 120 is used to improve the workability of the concrete if the water content is maintained resulting in minimal effect on strength. If the water content is reduced the flow can be maintained and a significant increase in strength can be achieved.

Benefits in Concrete

- Increased early and final strengths
- Reduced shrinkage
- Reduced permeability
- Increased density
- Reduced segregation and bleeding
- Flexible addition rates

Properties

Nature	Liquid
Colour	Dark Brown
Specific Gravity	1.12 g/cm ³
pH	6.50
Chloride Content	<0.10%
Na ₂ O equivalent	<1.00%

Addition Rates

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 800mls per 100 kg cement
(0.20% - 0.80% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

Standards

Optomix 120 complies with the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OPTOMIX 120

Water Reducing Plasticiser

Compatibility

Optomix 120 is compatible with all types of EN 197 cement systems.

Optomix 120 should not be pre-mixed with other admixtures and should be batched separately.

Storage

Optomix 120 should be stored undercover and protected from extreme temperatures, if stored unopened within the range 5°C and 30°C the product will have a minimum shelf life of 12 months.

Handling

Please refer to the **Optomix 120** Material Safety Data Sheet but in line with normal handling procedures, personal protective equipment should be worn.

Packaging

200 litre drums, 1000 litre IBCs and bulk deliveries.

Notes

Optomix 120 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix 120** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE Technical Department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd.
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286

Fax: +44 (0)1274 309143

e-mail: info@oscrete.co.uk

Website: www.oscrete.co.uk

PDS 7297 Rev 03 18/01/2016

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.