

OPTOMIX 450

High Range Superplasticiser

Description

Optomix 450 is a new generation superplasticiser based on a modified synthetic carboxylated polymer along with carefully selected synergistic materials, formulated to provide optimum performance in all classes of concrete. **Optomix 450** if correctly dosed will allow water reductions of between 12 to 36% whilst minimising workability loss.

Applications

Optomix 450 is particularly suitable for ready-mixed concrete where water reduction and slump retention are essential. The use of **Optomix 450** in difficult or complicated aggregate combinations and cement blends can be highly beneficial.

Benefits in Concrete

- Good workability retention
- Increased strengths
- Low water cement ratios
- Cost effective
- Flexible dosage

Properties

Nature	Liquid
Colour	Amber
Specific Gravity	1.05 g/cm ³
pH	7.00
Chloride Content	<0.10%
Na ₂ O equivalent	<1.00%

Addition Rates

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 1200mls per 100 kg cement
(0.2% - 1.20% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

Standards

Optomix 450 conforms to the requirements of BSEN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OPTOMIX 450

High Range Superplasticiser

Compatibility

Optomix 450 is compatible with all types of EN 197 cement systems.

Optomix 450 should not be pre-mixed with other admixtures and should be batched separately.

Storage

Optomix 450 should be stored undercover and protected from extreme temperatures, if stored unopened within the range 5°C and 30°C the product will have a minimum shelf life of 12 months.

Handling

Please refer to the **Optomix 450** Material Safety Data Sheet but in line with normal handling procedures, personal protective equipment should be worn.

Packaging

200 litre drums, 1000 litre IBCs and bulk deliveries.

Notes

Optomix 450 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix450** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE Technical Department for advice on admixture selection.

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd.
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286

Fax: +44 (0)1274 309143

e-mail: info@oscrete.co.uk

Website: www.oscrete.co.uk

PDS 7234 Rev 03 18/01/2016

