

OPTOMIX A61

Air Entraining Admixture

Description

Optomix A61 is a specially formulated blend of stabilised surface active agents designed to entrain controlled and stable quantities of air in mortars and screed. **Optomix A61** is a multi use product providing benefits in ready mixed concrete, mortar and screed.

Applications

Optomix A61 is used to entrain controlled and stable quantities of air into mortar which increases the durability of the finished product.

Benefits in Mortar & Screed

- Increased resistance to freeze thaw cycles
- Increases retention of mix water
- Reduces segregation
- Increases yield

Properties

Nature	Liquid
Colour	Amber
Specific Gravity	1.01 g/cm ³
pH	10.0
Chloride Content	<0.10%
Na ₂ O equivalent	<1.00%

Addition Rates

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

Mortar

160mls - 250mls per 100 kg cement
(0.16% - 0.25% by weight of cement)*
(0.40% - 0.70% BWC for mixes containing lime)

* These doses will produce air contents of between 15.0% - 18.0% in mortar, trials to determine this fact must be carried out before starting any new contract.

Standards

Optomix A61 complies with the requirements of BS EN 934-3 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OPTOMIX A61

Air Entraining Admixture

Compatibility

Optomix A61 is compatible with all types of EN 197 cement systems.

Optomix A61 should not be pre-mixed with other admixtures and should be batched separately.

Storage

Optomix A61 should be stored undercover and protected from extreme temperatures, if stored unopened within the range 5°C and 30°C the product will have a minimum shelf life of 12 months.

Handling

Please refer to the **Optomix A61** Material Safety Data Sheet but in line with normal handling procedures, personal protective equipment should be worn.

Packaging

200 litre drums, 1000 litre IBCs and bulk deliveries.

Notes

Optomix A61 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix A61** may be used after thawing slowly at room temperature followed by intensive remixing.

Optomix A61 if overdosed will result in an increase in air content and a reduction of strength, severe overdosing will result in the concrete being not fit for purpose.

Please consult the OSCRETE Technical Department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd.
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
e-mail: info@oscrete.co.uk
Website: www.oscrete.co.uk

PDS 6569 Rev 03 18/01/2016

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.