

OSCRETE MSP

Durable Sealant & Adhesive

TABLE OF CONTENTS

Description.....	1
Features.....	1
Usage.....	1
Application instructions.....	1
Application chart.....	2-3
Sound Insulation.....	4
Emission data indoor quality.....	4
Packaging.....	4
Limitations.....	4
Health and Safety.....	4
Technical data.....	5

DESCRIPTION

Oscrete MSP has excellent adhesion to non-porous surfaces, will bond to damp surfaces, seals under water and is paintable with most paints. This product is odourless, neutral and free of isocyanates. Conforms to ISO 11.600 F25 HM, EC No. 1935/2004 for materials intended to come into contact with food.

FEATURES

Oscrete MSP Sealant & Adhesive is suitable for sealing joints and assemblies in concrete and masonry applications. It can be used for adhering panels, boards and other insulation materials. In addition to its use in concrete and masonry applications, Oscrete MSP will seal and fix glass, porcelain, coated metal, epoxy and polyester panels, polystyrene, uPVC, stainless steel and anodised aluminium.

- Can be used for internal and external applications
- Bonds to damp surfaces

- Seals under water
- Contains fungicide
- Paintable with most paints
- Seals and bonds most substrates
- Excellent anti pick qualities
- Non staining
- Adhesives and sealant in one
- Can be used in food preparation areas
- FDA Approved
- Available in a range of colours
- CE Marked for glazing and sanitary applications

USAGE

Width x depth of joint x length (in linear metres) of joint, divide this by the volume of tube in ml equal number of cartridges required.

APPLICATION INSTRUCTIONS

All surfaces must be clean and sound, free from dirt, grease and other contamination.

Cut the cartridge seal and screw on the nozzle which should be cut to your required size. Using a skeleton gun, apply the sealant into the gap or joint to provide a good solid fill. If required place masking tape along edges, removing within 10 minutes of application. For gluing applications, apply adhesive in vertical lines at a distance of 30cm. Support the item that is being fixed for 24 hours until full curing occurs.

OSCRETE MSP

Durable Sealant & Adhesive

APPLICATION CHART

A = EXCELLENT B = GOOD C = FAIR

INTERNAL GENERAL AREAS	RATE
MASONRY	
Cementitious fibre	B
Concrete / Cellular concrete / Brick work	B
Granite / Marble / Natural stone	B
Plaster	B
WOOD	
Fibre board / veneer	B
Solid and untreated wood	A
GLASS / CERAMICS	
Ceramics / Porcelain	A
Glass	A
Layered glass	A
Reflective glass	A
METALS	
Copper and copper alloys	B
Iron	B
Lead	B
Stainless Steel	B
Untreated and anodised aluminium	B
Zinc	B
SYNTHETIC MATERIALS	
Acrylic / Fibreglass	A
PMMA (Plexiglas / Perspex)	B
Polycarbonate	B
Polyester	B
PVC and PVCu	A
OTHERS	
Acoustic sealing	A
Dry lining	B
Ductwork	B
Expansion joints	A
Frame fixing	B
Internal frame sealing	B
Low emission zones	B
Mirror Fixing	C
Plumbing	B
Polystyrene	B
Skirting & architraves	C
Stonework	B
Woodwork	B

BATHROOMS/SANITARY/PUBLIC BAT HOUSES	RATE
MASONRY	
Cementitious fibre	B
Concrete / Cellular concrete / Brick work	B
Granite / Marble / Natural stone	B
Plaster	B
GLASS / CERAMICS	
Ceramics / Porcelain	B
Glass	B
Layered glass	B
Reflective glass	B
METALS	
Copper and copper alloys	B
Stainless Steel	B
Untreated and anodised aluminium	B
Zinc	B
SYNTHETIC MATERIALS	
Acrylic / Fibreglass	B
PMMA (Plexiglas / Perspex)	B
Polycarbonate	B
Polyester	B
PVC and PVCu	B
OTHERS	
Acoustic sealing	B
Dry lining	B
Ductwork	B
Expansion joints	B
Frame fixing	B
Internal frame sealing	B
Low emission zones	B
Mirror fixing	B
Plumbing	B
Polystyrene	B
Skirting & architraves	B
Stonework	B
Woodwork	B

OSCRETE MSP

Durable Sealant & Adhesive

KITCHENS	RATE
Acoustic sealing	B
Concrete / Cellular concrete / Brick work	B
Dry Lining	B
Ductwork	B
Fibre board / veneer	B
Glass	B
Granite / Marble / Natural stone	B
Internal frame sealing	B
Plumbing	B
Professional food preparation areas	A
Skirting & architraves	B
Solid and untreated wood	B
Stainless steel	B
Untreated and anodised aluminium	B
Woodwork	B
EXTERNAL FACADES	RATE
MASONRY	
Concrete / Cellular concrete / Brick work	B
Granite / Marble / Natural stone	B
WOOD	
Fibre board / veneer	B
Solid and untreated wood	B
GLASS / CERAMICS	
Glass	A
Layered glass	A
Reflective glass	A
METALS	
Copper and copper alloys	B
Iron	B
Lead	B
Stainless steel	B
Untreated and anodised aluminium	B
Zinc	B
SYNTHETIC MATERIALS	
Acrylic / Fibreglass	A
PMMA (Plexiglas / Perspex)	A
Polycarbonate	A
PVC and PVCu	A
OTHERS	
Expansion joints	B
Leadwork	A
Plumbing	B
Polystyrene	A
Stonework	A

ROOFS	RATE
Bitumen	C
Copper and copper alloys	B
Expansion joints	B
Glass	A
Guttering	A
Layered glass	A
Lead	B
Leadwork	A
Plumbing	B
PMMA (Plexiglas / Perspex)	A
Polycarbonate	A
Polystyrene	A
Reflective glass	A
Stainless steel	B
Stonework	A
Untreated and anodised aluminium	B
Woodwork	B
Zinc	B

Due to the diversity of applications and substrates Oscrete cannot accept responsibility for results obtained using this chart. It is suggested a preliminary test be carried out first to check bond and seal.

OSCRETE MSP

Durable Sealant & Adhesive

SOUND INSULATION

Oscrete MSP has been tested at BM Trada (UKAS accredited); according to EN ISO 10140- 2:2010. Usage of any backing material is optional, due to the tests being conducted with sealant only

Description	Sound Reduction
Single sided seal ≥ 12 mm depth	62dB
Double sided seal ≥ 12 mm depth	>62dB

EMISSION DATA INDOOR AIR QUALITY

COMPOUND	EMISSION RATE AFTER 3 DAYS	EMISSION RATE AFTER 4 WEEKS
TVOC	40 $\mu\text{g}/\text{m}^3$	< 5 $\mu\text{g}/\text{m}^3$
TSVOC	n.d	n.d. (< 5 $\mu\text{g}/\text{m}^3$)
VOC w/o NIK	n.d	n.d. (< 5 $\mu\text{g}/\text{m}^3$)
R Value	< 1	< 1
Formaldehyde	< 3 $\mu\text{g}/\text{m}^3$	< 3 $\mu\text{g}/\text{m}^3$
Acetaldehyde	< 3 $\mu\text{g}/\text{m}^3$	< 3 $\mu\text{g}/\text{m}^3$
Sum for+ace	< 0.002 ppm	-
Carcinogenic	n.d. (< 1 $\mu\text{g}/\text{m}^3$)	n.d. (< 1 $\mu\text{g}/\text{m}^3$)

n.d. = not detected

Oscrete MSP complies with the requirements of GEV and the results correspond to the EMICODE emission class EC 1PLUS which is the best possible environmental and indoor hygiene health protection mark.

Tested by Eurofins Product Testing, report number 392- 2014-00011601_B.

PACKAGING

Oscrete MSP is supplied in 600ml foil cartridges, 12 cartridges per carton.

LIMITATIONS

Oscrete MSP is not recommended for application on PE, PP, Teflon, wax, neoprene and bituminous surfaces. Not suitable for underwater applications, use with aquaria or expansion joints. Not paintable with alkyd resin based paint. Not suitable for vertical joints. Not suitable for applications in direct contact with sealing of insulation glass or in direct contact with PVB foil or coat glass. On porous surfaces such as concrete a primer is recommended. Yellowing can occur in the dark. Clear sealant is not UV resistant or suitable for use on natural stone. It is the user's responsibility to determine suitability. Adhesion tests prior to application are recommended. Store between +5°C and +25°C in cool dry conditions.

HEALTH AND SAFETY

Wash the material from the skin while still wet. Material in contact with eyes should be washed out immediately with water. Seek medical advice if discomfort persists. More detailed information can be found in the relevant Oscrete MSP Material Safety Data Sheet

OSCRETE MSP

Durable Sealant & Adhesive

TECHNICAL DATA

		WHITE	CLEAR
Slump ISO 7390	mm	<2	<2
Density	g/ml	1,53	1,06
Skin forming time 23°C/55%RH	min	10	10
Max movement allowed ISO 9040	%	20	20
Temperature resistance after curing	°C	-30 to 100 °C	-30 to 100 °C
Shrinkage		nil	nil
Curing (24 hours) 23°C/55%RH	mm	02/03	2
Mechanical properties 2mm film			

Hardness, Shore A DIN 53505		60	45
Modulus, 100% DIN 53504	MPa	1,35	1,15
Tensile strength DIN 53504	MPa	2,20	2,40
Elongation at break DIN 53504	%	300	250

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd.
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
e-mail: info@oscrete.co.uk
Website: www.oscrete.co.uk

PDS 7907 Rev 00 19/05/2016