

ALPHAFLOW BIND-IT

Viscosity Modifying Admixture

Description

Alphaflow Bind-It is a liquid admixture based on an inorganic water based colloidal silica. **Alphaflow Bind-It** is used to control the stability, segregation and water loss in highly fluid concretes. The fine particles start to work as soon as they are added to the concrete mix adding texture to the cement paste.

Applications

Alphaflow Bind-It is used in high workable concretes such as self compacting concrete, high workability concrete or where excess water needs to be absorbed. Due to its fine particle size **Alphaflow Bind-It** improves the aggregate grading and helps prevent segregation and bleeding, it will also improve the surface finish characteristics.

Benefits in Concrete

- Improves cohesion
- Reduces pump pressures
- Reduces segregation
- Reduces porosity
- Corrects gap grading issues
- Improves surface finish



Properties

Nature	Liquid
Colour	Milky White
Specific Gravity	1.30g/cm ³
pH	9.5
Chloride Content	<0.10%
Na ₂ O equivalent	<1.00

Addition Rates

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

250 mls - 2000 mls per 100 kg cement
(0.25% - 2.00% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

Standards

Alphaflow Bind-It conforms to the requirements of BSEN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



ALPHAFLOW BIND-IT

Viscosity Modifying Admixture

Compatibility

Alphaflow Bind-It is compatible with all types of EN 197 cement systems.

Alphaflow Bind-It should not be pre-mixed with other admixtures and should be batched separately.

Storage

Alphaflow Bind-It should be stored undercover and protected from extreme temperatures, if stored unopened within the range 5°C and 30°C the product will have a minimum shelf life of 12 months.

Handling

Please refer to the **Alphaflow Bind-It** Material Safety Data Sheet but in line with normal handling procedures, personal protective equipment should be worn.

Packaging

200 litre drums, 1000 litre IBCs and bulk deliveries.

Notes

Alphaflow Bind-It should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

Alphaflow Bind-It cannot be reconstituted after freezing, the product will split and be unfit for use.

Please consult the OSCRETE Technical Department for advice on admixture selection.

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd.
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286

Fax: +44 (0)1274 309143

e-mail: info@oscrete.co.uk

Website: www.oscrete.co.uk

PDS 7316 Rev 03 18/01/2016