

AQUAPEL EFX

Water Resisting Admixture

PRODUCT DESCRIPTION

Aquapel EFX is a new generation water repellent based on a modified poly-siloxane blend. **Aquapel EFX** is designed to provide exceptional water repellency in concrete and provides benefits in all types of precast concrete, particularly block paving. The blend of silane/siloxane in **Aquapel EFX** has been chosen due to its effective ability in preventing the leaching from concrete of soluble salts, commonly termed efflorescence. In controlling water absorption and efflorescence **Aquapel EFX** increases the durability of concrete and prevents the long term colour degradation of decorative coloured concrete.

APPLICATIONS

Aquapel EFX is mainly used in dry/semi-dry concrete to reduce water absorption and reduce efflorescence, it can also be used in wet cast concrete to achieve the same performance.

BENEFITS

- Improved durability.
- Reduced permeability.
- Increased water tightness.
- Reduced efflorescence.
- Colour enhancement

PROPERTIES

Nature:	Liquid
Appearance:	White
Specific Gravity: (20°C)	1.00 g/cm ³
pH:	6.5
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 1.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls—1000mls per 100kg cement

(0.20% - 1.00% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE technical department for further advice.

STANDARDS

Aquapel EFX conforms to the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



AQUAPEL EFX

Water Resisting Admixture

COMPATIBILITY

Aquapel EFX is compatible with all types of EN 197 cement systems.

Aquapel EFX should not be premixed with other admixtures and should be batched separately.

STORAGE

Aquapel EFX should be protected from extreme temperature, frost and direct sunlight, the product has a minimum shelf life of 12 months.

HANDLING

Please refer to the **Aquapel EFX** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

PACKAGING

200 litres drums, 1000 litre IBC's and bulk deliveries.

NOTES

Aquapel EFX should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Aquapel EFX** may be used after thawing, slowly at room temperature followed by intensive mixing.

Aquapel EFX should be regularly circulated to ensure complete homogeneity.

Please consult the OSCRETE technical department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
E-mail: info@oscrete.com
Website: www.oscrete.com

PDS 7779 Rev 04 01/01/2020



OSCRETE
CONSTRUCTION PRODUCTS