

OPTOMIX 210

Water Reducing Plasticiser

PRODUCT DESCRIPTION

Optomix 210 is an economical high range water reducer based upon blended polycarboxylate ethers, it is designed to improve both the workability and strength of concrete with minimal effect on other properties. **Optomix 210** if used correctly can achieve water reductions above 20%.

APPLICATIONS

Optomix 210 is used to improve the workability of the concrete if the water cement ratio is maintained resulting in minimal effect on strength. If the water content is reduced the flow can be maintained and a significant increase in strength can be achieved.

BENEFITS

- Increased early and final strengths.
- Reduced shrinkage.
- Reduced permeability.
- Increased density.
- Reduced segregation & bleeding.
- Flexible addition rates.

PROPERTIES

Nature:	Liquid
Appearance:	Light Amber
Specific Gravity: (20°C)	1.075 g/cm ³
pH:	6.5
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 1.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 1200mls per 100 kg cement
(0.20% - 1.20% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

STANDARDS

Optomix 210 complies with the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OPTOMIX 210

Water Reducing Plasticiser

COMPATIBILITY

Optomix 210 is compatible with all types of EN197 cement systems.

Optomix 210 should not be pre-mixed with other admixtures and should be batched separately.

STORAGE

Optomix 210 should be stored undercover and protected from extreme temperatures, if stored between the range 5°C to 30°C the product will have a minimum shelf life of 12 months.

HANDLING

Please refer to the **Optomix 210** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

Refer to the Material Safety Data Sheet for full details.

PACKAGING

200 litre drums, 1000 litre IBC's and bulk deliveries.

NOTES

Optomix 210 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix 210** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE technical department for advice on admixture selection.

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
E-mail: info@oscrete.com
Website: www.oscrete.com

PDS 7656 Rev 04 01/01/2020



OSCRETE
CONSTRUCTION PRODUCTS