

OPTOMIX 460

High Range Slump Retention Superplasticiser

PRODUCT DESCRIPTION

Optomix 460 is a new generation slump retention superplasticiser based on modified synthetic carboxylated polymer and carefully selected synergised materials formulated to provide optimum performance in all classes of concrete. **Optomix 460** if used correctly can achieve water reductions above 20% whilst minimising workability loss.

APPLICATIONS

Optomix 460 is particularly suitable for ready-mixed concrete where water reduction and slump retention are essential. The use of **Optomix 460** in difficult or complicated aggregate combinations and cement blends can be highly beneficial.

BENEFITS

- Very high workability retention.
- Increased early and final strengths.
- Good workability retention.
- Low water/cement ratios.
- Cost effective.
- Flexible addition rates.

PROPERTIES

Nature:	Liquid
Appearance:	Amber
Specific Gravity: (20°C)	1.06 g/cm ³
pH:	4.50
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 1.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 1200mls per 100 kg cement
(0.20% - 1.20% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

STANDARDS

Optomix 460 complies with the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OPTOMIX 460

High Range Slump Retention Superplasticiser

COMPATIBILITY

Optomix 460 is compatible with all types of EN197 cement systems.

Optomix 460 should not be pre-mixed with other admixtures and should be batched separately.

STORAGE

Optomix 460 should be stored undercover and protected from extreme temperatures, if stored between the range 5°C to 30°C the product will have a minimum shelf life of 12 months.

HANDLING

Please refer to the **Optomix 460** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

Refer to the Material Safety Data Sheet for full details.

PACKAGING

200 litre drums, 1000 litre IBC's and bulk deliveries.

NOTES

Optomix 460 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix 460** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE technical department for advice on admixture selection.

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
E-mail: info@oscrete.com
Website: www.oscrete.com

PDS 7918 Rev 01 01/01/2020


OSCRETE
CONSTRUCTION PRODUCTS