

# OPTOMIX SRA

## Shrinkage Reduction Admixture

### PRODUCT DESCRIPTION

**Optomix SRA** is a ready to use liquid based admixture specifically designed to reduce drying shrinkage, curling, dimensional stability and the potential for subsequent cracking in concrete and mortar. **Optomix SRA** acts directly on the shrinkage causing mechanism at the time of the cement hydration whilst reducing capillary tension of pore water in the concrete voids. This action substantially reduces the drying shrinkage associated with concrete. **Optomix SRA** does not contain added chlorides and will not promote the corrosion of steel.

### APPLICATIONS

**Optomix SRA** is particularly suitable for large scale concrete floors where shrinkage needs to be minimised.

### BENEFITS

- Improved aesthetics.
- Good workability retention.
- Reductions in early shrinkage.
- Reduced cracking.
- Thinner sections.
- Extended joint spacings.

### PROPERTIES

Nature:	Liquid
Appearance:	Light Amber
Specific Gravity: (20°C)	1.012 g/cm <sup>3</sup>
pH:	7.00
Chloride Content:	< 0.10
Alkali Content (Na <sub>2</sub> O):	< 1.00

### ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

500mls - 2000mls per 100 kg cement  
(0.50% - 2.00% by weight of cement)

### STANDARDS

**Optomix SRA** is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



# OPTOMIX SRA

## Shrinkage Reduction Admixture

### COMPATIBILITY

**Optomix SRA** is compatible with all types of EN197 cement systems.

**Optomix SRA** should not be pre-mixed with other admixtures and should be batched separately.

### STORAGE

**Optomix SRA** should be stored undercover and protected from extreme temperatures, if stored between the range 5°C to 30°C the product will have a minimum shelf life of 12 months.

### HANDLING

Please refer to the **Optomix SRA** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

Refer to the Material Safety Data Sheet for full details.

### PACKAGING

200 litre drums, 1000 litre IBC's and bulk deliveries.

### NOTES

**Optomix SRA** should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Optomix SRA** at temperatures below 5°C may form small crystals, but do not affect the performance of the product. **Optomix SRA** can be used after thawing slowly at room temperature followed by intensive re-mixing.

Please consult the OSCRETE technical department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd  
Rutland Street  
Bradford  
West Yorkshire  
BD4 7EA  
United Kingdom

#### Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

Telephone: +44 (0)1274 393286  
Fax: +44 (0)1274 309143  
E-mail: [info@oscrete.com](mailto:info@oscrete.com)  
Website: [www.oscrete.com](http://www.oscrete.com)

PDS 7760 Rev 04 01/01/2020



**OSCRETE**  
CONSTRUCTION PRODUCTS