

OSPAVE 170

Water Reducing Air-Entraining Plasticiser

PRODUCT DESCRIPTION

Ospave 170 is an economical normal range water reducer based upon blended modified lignosulphonates and carefully selected surfactants. It is designed to entrain controlled and stable quantities of air in concrete mixes, whilst providing all the benefits of a normal range water reducing plasticiser. **Ospave 170** if used correctly can achieve water reductions of up to 15%.

APPLICATIONS

Ospave 170 is used to improve the workability and durability of concrete if the water cement ratio is maintained resulting in minimal effect on strength. It is also used in extruded concrete where the concrete is formed as it is placed. When using **Ospave 170** in concrete at over 50mm slump a controlled amount of stable air will be entrained, in many cases the strength drop that occurs with air-entrained concrete will be negated by the plasticising action of the admixture.

BENEFITS

- Increased resistance to freeze-thaw cycles.
- Improved surface finish.
- Increased durability of concrete.
- Reduced segregation and bleeding.
- Less shrinkage.

PROPERTIES

Nature:	Liquid
Appearance:	Dark Brown
Specific Gravity: (20°C)	1.15 g/cm ³
pH:	8.0
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 1.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

300mls - 600mls per 100 kg cement
(0.30% - 0.60% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

STANDARDS

Ospave 170 is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



OSPAVE 170

Water Reducing Air-Entraining Plasticiser

COMPATIBILITY

Ospave 170 is compatible with all types of EN197 cement systems.

Ospave 170 should not be pre-mixed with other admixtures and should be batched separately.

STORAGE

Ospave 170 should be stored undercover and protected from extreme temperatures, if stored between the range 5°C to 30°C the product will have a minimum shelf life of 12 months.

HANDLING

Please refer to the **Ospave 170** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

Refer to the Material Safety Data Sheet for full details.

PACKAGING

200 litre drums, 1000 litre IBC's and bulk deliveries.

NOTES

Ospave 170 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Ospave 170** may be used after thawing slowly at room temperature followed by intensive remixing.

Ospave 170 if overdosed will result in an increase in workability, set retardation and air content. The amount of increase will depend on the actual overdose, the temperature and the materials used, care should be made when batching to dispense the correct addition.

Please consult the OSCRETE technical department for advice on admixture selection.

OSCRETE is a division of Christeyns UK Ltd
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

Telephone: +44 (0)1274 393286
Fax: +44 (0)1274 309143
E-mail: info@oscrete.com
Website: www.oscrete.com

PDS 7300 Rev 04 01/01/2020



OSCRETE
CONSTRUCTION PRODUCTS