

# SIGMA 120

## Masonry Block Water Reducer

### PRODUCT DESCRIPTION

**Sigma 120** is an economical normal range water reducer based upon blended modified lignosulphonates. It is designed to improve both the workability of concrete with minimal effect on other properties. **Sigma 120** if used correctly can achieve water reductions of up to 16%.

### APPLICATIONS

**Sigma 120** can be used to reduce the water content in dry/semi-dry concrete which in turn will increase the density of the finished product leading to higher strengths.

### BENEFITS

- Increased early and final strengths.
- Reduced shrinkage.
- Reduced permeability.
- Increased density.
- Reduced segregation & bleeding.

### PROPERTIES

Nature:	Liquid
Appearance:	Dark Brown
Specific Gravity: (20°C)	1.12 g/cm <sup>3</sup>
pH:	6.5
Chloride Content:	< 0.10
Alkali Content (Na <sub>2</sub> O):	< 1.00

### ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

200mls - 800mls per 100 kg cement  
(0.20% - 0.80% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE Technical department for further advice.

### STANDARDS

**Sigma 120** complies with the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



# SIGMA 120

## Masonry Block Water Reducer

### COMPATIBILITY

**Sigma 120** is compatible with all types of EN197 cement systems.

**Sigma 120** should not be pre-mixed with other admixtures and should be batched separately.

### STORAGE

**Sigma 120** should be stored undercover and protected from extreme temperatures, if stored between the range 5°C to 30°C the product will have a minimum shelf life of 12 months.

### HANDLING

Please refer to the **Sigma 120** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

Refer to the Material Safety Data Sheet for full details.

### PACKAGING

200 litre drums, 1000 litre IBC's and bulk deliveries.

### NOTES

**Sigma 120** should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Sigma 120** may be used after thawing slowly at room temperature followed by intensive remixing.

Please consult the OSCRETE technical department for advice on admixture selection.

#### Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

OSCRETE is a division of Christeyns UK Ltd  
Rutland Street  
Bradford  
West Yorkshire  
BD4 7EA  
United Kingdom

Telephone: +44 (0)1274 393286  
Fax: +44 (0)1274 309143  
E-mail: [info@oscrete.com](mailto:info@oscrete.com)  
Website: [www.oscrete.com](http://www.oscrete.com)

PDS 7297 Rev 04 01/01/2020



**OSCRETE**  
CONSTRUCTION PRODUCTS